Dingo Cement Pty Ltd
Unit 8, 25-37 Huntingdale Rd
Burwood VIC 3125. Australia

Phone: +61 (3) 8080 1420
info@dingocement.com.au
www.dingocement.com.au

PRODUCT DATA SHEET

Version May 2026

BITUMEN RESURFACER

A versatile, rapid-setting cement-based resurfacer designed for Bitumen restoration and repair. Formulated with a polymer-modified cement blend and specialised additives, it closely matches the appearance of existing bitumen. When mixed with water, it produces a durable, high-quality resurfacing solution with excellent bonding strength. It can also be used on concrete surfaces. Working time is approximately 20 minutes, and the surface can be reopened to traffic in just 2 hours.

Key Features

- ✓ Makes your Bitumen surface look like new
- ✓ Easy to use - Just add water, mix and trowel to your desired finish
- ✓ Drive on in 2 hours

Popular Uses

- ✓ Driveways
- ✓ Potholes
- ✓ Footpaths
- ✓ Parking areas
- ✓ General repairs

Directions for use

PLEASE READ CAREFULLY BEFORE OPENING PACKAGING

Surface Preparation

- Ensure the substrate is clean, sound, and free of contamination
- Remove loose material and roughen the surface
- Pressure washing is recommended for maximum adhesion
- Eliminate standing water before placement

Mixing

- Use mechanical mixing equipment (mixer or drill-mounted paddle)
- For 10kg of dry product: add 2 - 2.2 Litres of clean water
- Mix for 1–3 minutes until smooth and a uniform consistency

Application

- Use promptly after mixing
- Finish with trowel, float, loop roller, or broom to match existing surface texture
- Apply in thickness from 3mm up to 50mm
- Do not apply in multiple layers
- For deeper repairs, extend with clean coarse aggregate (up 1.9 cm) to achieve thickness up to 61 cm.
- Can be used at air temperatures between 5?C–35?C.

Safety

- Avoid inhaling dust; use in well-ventilated areas.
- Cement dust may irritate eyes, skin, and lungs.
- Wear goggles, gloves, and protective clothing.
- Use a NIOSH/MSHA-approved respirator (P-, N-, or R-95).
- Wash off dust or wet cement immediately with soap and water.
- In case of eye contact, flush with clean water for 15 minutes and seek medical care

Yield

10kg of Bitumen Resurfacer will cover approx. 1m2 at a depth of 4m